



TECSOM 3630S SUPREME ACOUSTIQUE SPECIAL

Factory ISO 9001 Quality Management System
 Factory ISO 14 001 Environmental Management System
 Factory OHSAS 18001 Health, Safety and Security Management System

SPECIFICATIONS					Article n° : 17254050A-00XXX		
DESCRIPTION	NORM	DATA		35 colors	Reflectance Index (%)		
Composition fibreuse / Pile Fibre		100% Polyamide (Solution dyed)		(DA019) / 019	4,7%		
Jauge / Gauge		1/10 loop pile		(DA707) / 017	9,0%		
Serrage / Number of Stitches	ISO 1763	41/dm		(DB016) / 026*	7,2%		
Densité / Tuft Density	ISO 1763	168 100 Stitches/m ²		(DB024) / 024	9,9%		
Poids de fil / Total pile mass	ISO 8543	740 g/m ²		(DB127) / 027	8,0%		
Masse de velours utile / Mass of pile above the substrate	ISO 8543	450 g/m ²		(DB202) / 022*	14,0%		
Epaisseur velours utile / Thickness of pile above the substrate	ISO 1766	3,8 mm		(DB208) / 028	6,8%		
Densité du velours de surface / Surface pile density	ISO 8543	0,1185 g/cm ³		(DB309) / 029	5,8%		
Masse totale / Total Weight	ISO 8543	5285 g/m ²		(DE507) / 127	16,3%		
Epaisseur totale / Total Thickness	ISO 1765	10 mm		(DG008) / 038*	11,0%		
Premier dossier / Primary Backing		Non tissé / Non woven primary backing		(DG304) / 034*	17,3%		
Envers / Backing		Backing System avec renfort acoustique en fibres PES Matières recyclées renforcées par un voile de verre 100 % recycled vinyl backing reinforced with glass fiber		(DG607) / 037*	11,3%		
				(DJ307) / 107	14,9%		
				(DL007) / 137	2,1%		
Dimensions / Tile Size		50x50cm		(DL012) / 132*	16,7%		
Dalles par boîte / Tiles per Box		16 = 4 m ²		(DL118) / 138	7,2%		
				(DL209) / 139	6,3%		
Sens de pose / Installation				(DM101) / 041	15,1%		
				(DM105) / 045	10,6%		
Base d'impression / Printing facilities				(DM207) / 047	9,8%		
				(DM409) / 049	6,7%		
TECHNICAL PERFORMANCES							
Classification (EN 1307)	Class: 33 - Commercial Heavy LC1				(DO125) / 055	18,6%	
Classement UPEC (Référentiel NF 262)	Classement: Certificat n°:				(DR055) / 095	12,7%	
 Fire rating	EN 13501-1		 Impact noise reduction	ISO 717/2	ΔL _(w) = 28 dB	(DS110) / 060	26,4%
	CflS1		 Sound absorption	ISO 11654	α _w = 0,30	(DS012) / 062*	20,1%
 Electrostatic properties	ISO 6356	≤ 2,0kV	 Colour Fastness	EN 105 - B02	7/8	(DT005) / 075	13,3%
			 Castor Chair	EN 985	Passed R _{≥2,4}	(DT408) / 078	9,9%
	ISO 10965	RT ≈ 10 ¹⁰ Ω	 Heated Floor	ISO 10456	0,15 m ² K/W	(DV008) / 088	8,4%
 Dimensional Stability	EN 986			N° 0679-CPR-1036 15 EN 14041: 2004 EN1307	932	31,4%	
	≤ 0,10%						DS 1853/5
ENVIRONMENTAL ISSUES							
 ÉMISSIONS DANS L'AIR INTÉRIEUR A+			LEED: This product contributes to obtain points towards MR2, MR4, MR5, IEQ4.1 and IEQ4.3 credits to the LEED certification of your buildings.				

Les informations ci-dessus peuvent subir des modifications au profit d'une future amélioration / The above information is subject to modifications for the benefit of further improvement.
 Updated on 15/01/2015